

White Lightning® Asphalt Roof Cement

Physical Properties:

Type:	Roof Cement
Color:	Black
Shelf Life:	12 months
Flash Point:	107°F
Cure Time:	24-48 hours
Application Temperature:	Above 32°F
Service Temperature:	-40°F to 180°F
Mildew Resistance:	Good
Water Resistance:	Excellent
Odor:	Solvent Like
Shrinkage:	Low
Vehicle:	Solvent Based
Weight/Gallon:	8.6 lbs./gal

Performance Data:

Joint Movement Capability:	Moderate
Joint Size:	1/8" X 1/8" to _" X _"
Freeze-Thaw Stability:	Stable through 5 cycles
Clean Up:	Mineral Sprits
Flexibility:	Excellent
Painting:	Do not paint

Surface Preparation: All surfaces should be clean and free from oil, grease, rust, dirt, and other foreign matter. Excess water should be removed, if possible, before application of Asphalt Roof Cement.

Cautions: Do not use near open flame. Avoid breathing solvent fumes and prolonged contact with skin. Do not take internally. If swallowed, do not induce vomiting. Call a physician immediately. Keep out of reach of children. Keep container covered when not in use. Do not thin. Dispose of in an environmentally safe manner.

Specifications:

*ASTM D-2822 Type I

*Federal Specification SS-C-153 Type I

Packaging:

Color	Order #	UPC	Size
Black	WL00215	0-23275-00215-9	10.0 fl oz.

For more information please call or write:
White Lightning Products
101 Prospect Ave. NW
Cleveland, OH 44115
1-800-241-5295

